Technical data sheet



Pullex Bodenöl 4402

Solvent-based, piqmented oil for horizontal wooden surfaces in outdoor areas, for DIY and trade

PRODUCT DESCRIPTION

General

Water-repellent, highly penetrating oil for horizontal wooden surfaces in outdoor areas (open-pore). Protects hardwoods and softwoods from soiling and moisture. Allows the wood to breathe and reduces swelling and shrinkage.

Stand-out features of this product include excellent accentuation of the wood grain and ease of use with no visible brush strokes or roller marks. Micronised special pigments guarantee very good weathering and UV resistance as well as outstanding colour stabilisation of exotic woods. Without the addition of aromatic solvents.

Special properties and standards

 The coating is protected against blue stain and mould by a biocidal active substance.

Active substance:

2.4 g/kg (0.24 %) 3-lod-2-propinylbutylcarbamat

Application area



For horizontal wooden surfaces that are not dimensionally stable for exterior use, such as balcony floors, landing stages, terraces, etc.

Particularly suitable for types of wood such as larch and exotic types of wood such as Bangkirai, Teak and Massaranduba.

PROCESSING

Processing instructions





- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least + 5 °C.
- The optimal conditions for use are between 15 30 °C with a relative atmospheric humidity between 40 - 80 %.
- Do not process it under conditions of intense sunlight, rain, extremely high humidity, strong wind or pending frost.
- Attention: Care should be taken to sand the wood uniformly and to apply the product evenly!
- The formation of a film must be avoided at all costs!
- Resin flow cannot be avoided by the coating.
- It is optimal to apply a coating on all sides prior to installation. Following
 it is recommended to seal the cut edges using Allwetterlack (4502) (2
 coats).
- Residual plaster (high level of alkalinity) or ferrous dust (rust formation) may lead to black discoloration on larch wood and other types of wood rich in extracts.

- The formation of "footprint marks" is natural in case of highly frequented surfaces. These may, however, be eliminated with ease using regular preservative coatings (see preservative coat).
- Any change in the processing sequence, environmental conditions, nonobservance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems as well as to impairments with regard to weathering and color stability.
- Please follow our ARL 500 Working guideline for coating nondimensionally stable and limited dimensionally stable construction elements - General part.
- Please follow our ARL 505 Working guideline for alkyd resin coatings/glazes and oils.

Application technique





	Brushing
Applied quantity per application (ml/m²)	60 - 80

The product is ready to use.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

For good thorough drying, the recommended application quantities must be adhered to. Excessive layer thicknesses lead to a considerable drying delay!

Drying times

(at 23 °C and 50 % rel. humidity)



Recoatable	12 h
------------	------

The figures given above are reference values.

The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

To ensure perfect drying, good room ventilation must be provided. Low ventilation, e.g. from dense stacking, delays drying.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

On types of woods rich in extracts (such as oak, iroko), drying may be delayed.

Cleaning the working equipment



With Adlerol-Terpentinölersatz (7231) immediately after use.

SUBSTRATE

Type of substrate

Fine-pored and coarse-pored hardwoods and softwoods.

Thermowood treated wood.

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

A prerequisite for ensuring long durability of the coating is to observe the basic principles of constructional wood preservation.

	Please observe the additional documents:
	● ÖNORM B 3430-1
	● ÖNORM B 2230-1
	• DIN 18363
	BFS data sheet no. 18.
Wood moisture	Hardwoods: 12 ± 2 %
	Softwoods: 15 ± 2 %
Substrate preparation	For optimal durability we recommend to sand smooth wooden surfaces with grain size 80 – 120 in the direction of the fibre, clean thoroughly and remove wood extractives such as, for example, resins and resin pockets. Round off any sharp edges.
	A prerequisite for ensuring long durability of the coating is to observe the basic principles of constructional wood preservation.
	Clean resin-rich woods and exotic woods with drying retardants with Nitro-Verdünner 8017 (8017).
	COATING SYSTEM
Primer coat	1 x Pullex Bodenöl (4402)
	Intermediate drying: approx. 12 hour(s)
Finishing coat	1 x Pullex Bodenöl (4402)
	MAINTENANCE
	The development are covered for these include neutral and the terms
Care	The durability depends on several factors: these include particularly the type of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary.
Care	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance
Care Maintenance	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x
	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x using Pullex Bodenöl (4402). Avoid film formation at all costs! Sand weathered or greyed wood until the raw wood. Further processing as
	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x using Pullex Bodenöl (4402). Avoid film formation at all costs! Sand weathered or greyed wood until the raw wood. Further processing as per new coating (see coating system). On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals
	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x using Pullex Bodenöl (4402). Avoid film formation at all costs! Sand weathered or greyed wood until the raw wood. Further processing as per new coating (see coating system). On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals must be expected.
Maintenance	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x using Pullex Bodenöl (4402). Avoid film formation at all costs! Sand weathered or greyed wood until the raw wood. Further processing as per new coating (see coating system). On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals must be expected. ORDERING INFORMATION 750 ml, 2.51 Standard colour(s): Java (4402057056)
Maintenance Size of trading unit	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x using Pullex Bodenöl (4402). Avoid film formation at all costs! Sand weathered or greyed wood until the raw wood. Further processing as per new coating (see coating system). On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals must be expected. ORDERING INFORMATION 750 ml, 2.51 Standard colour(s):
Maintenance Size of trading unit Colour shades / Glosslevels	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x using Pullex Bodenöl (4402). Avoid film formation at all costs! Sand weathered or greyed wood until the raw wood. Further processing as per new coating (see coating system). On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals must be expected. ORDERING INFORMATION 750 ml, 2.51 Standard colour(s): Java (4402057056) Kongo (4402057069)
Maintenance Size of trading unit Colour shades / Glosslevels	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x using Pullex Bodenöl (4402). Avoid film formation at all costs! Sand weathered or greyed wood until the raw wood. Further processing as per new coating (see coating system). On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals must be expected. ORDERING INFORMATION 750 ml, 2.51 Standard colour(s): Java (4402057056) Kongo (4402057069) Lärche (4402085967) Other colour shades can be obtained using the ADLER colour mixing system
Maintenance Size of trading unit Colour shades / Glosslevels	of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 x using Pullex Bodenöl (4402). Avoid film formation at all costs! Sand weathered or greyed wood until the raw wood. Further processing as per new coating (see coating system). On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals must be expected. ORDERING INFORMATION 750 ml, 2.5 1 Standard colour(s): Java (4402057056) Kongo (4402057056) Kongo (4402057069) Lärche (4402085967) Other colour shades can be obtained using the ADLER colour mixing system Color4You. Base paint(s):

In order to ensure uniformity of the colour shade, use only material with the same batch number on a given surface.

Apply exclusively pigmented colour shades to ensure a good weather resistance.

Please consume blended products within 3 months.

Supplementary products

Adlerol-Terpentinölersatz (7231) Nitro-Verdünner 8017 (8017) Allwetterlack (4502)

Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS

Durability / storage



Min. 3 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 $^{\circ}$ C).

Close opened containers well and use up the content as soon as possible.

We recommend to transfer the contents of open containers to smaller ones in order to prevent gelling / skin formation.

Giscode

Ö60

Safety information



When using cloths that have been soaked with oxidative drying products, there is a risk of spontaneous combustion! Spread soaked cloths out and let them dry; it is necessary to store them in sealed metal containers or under water.

When sanding, use at least a P2 dust filter as personal safety equipment to protect against abrasive and wood dust. In case of hardwood (especially for Beech, Oak) a dust filter P3 is recommended.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com**.