

Pullex Color

4403

Solvent-based, opaque wood glaze for DIY and trade

	PRODUCT DESCRIPTION		
General	Universal, silky matt, opaque wood glaze formulated with high-quality, long- oil binding agents, for exterior use. Very good weathering resistance, vapour-permeable, moisture-regulating, environmentally friendly on account of its high solids content. The product is low-odour due to the use of petroleum spirits that are free from aromatic hydrocarbons as solvents.		
Special properties and standards	• The coating is protected against blue stain and mould by a biocida active substance.		
	Active substance: 2.4 g/kg (0.24 %) 3-Iod-2-propinylbutylcarbamat		
Application area	For non-dimensionally stable and limited dimensionally stable timber components for exterior use, such as e.g. wooden houses, timber cladding, canopies, profile boards, window shutters, balconies, gates.		
	For dimensionally stable timber components for exterior and interior use such as e.g. wooden windows and front doors.		
	For new coatings and particularly for the renovation of exterior wood.		
	PROCESSING		
Processing instructions	• Please stir the product before use.		
	 The temperature of the product and object, and the room temperature must be at least + 5 °C. 		
	 The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %. 		
	 Do not process it under conditions of intense sunlight, rain, extremely high humidity, strong wind or pending frost. 		
	• For new timber components we recommend an all-over coating.		
	 Apply a thin coat to horizontal wooden parts to avoid flaking due to excessive layer thickness. 		
	 Resin flow cannot be avoided by the coating. 		
	 Water-soluble wood extracts can be leached particularly by driving rain. This can be minimized by an all-over coating and additional sealing of the end grains. 		
	 Any change in the processing sequence, environmental conditions, non- observance of instructions or the use of products not listed may have ar unfavourable effect on the result. Deviations lead to film and adhesior problems as well as to impairments with regard to weathering and color stability. 		

1-0 IMC 4403 | 04/25

ADLER-Werk Lackfabrik, A-6130 Schwaz Fon: +43/5242/6922-190, Fax: +43/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions are based on the current state of knowledge and are intended to advise the buyer/user to the best of our knowledge, but must be individually adapted to the areas of application and processing conditions. The buyer/user is responsible for deciding on the suitability and use of the supplied product, which is why we recommend that a sample be produced to check the suitability of the product. In all other respects, our General Terms and Conditions of Sale apply. All previous data sheets lose their validity with this edition. We reserve the right to make changes to container sizes, color shades and available gloss levels.

- Please follow our ARL 500 Working guideline for coating nondimensionally stable and limited dimensionally stable construction elements – General part.
- Please follow our ARL 300 Working guideline for coating dimensionally stable and limited dimensionally stable construction elements General part along with all standards and guidelines for window construction.
- Please follow our ARL 340 Wood preservation of dimensionally stable and limited dimensionally stable components in accordance with DIN 68800.
- Please follow our ARL 505 Working guideline for alkyd resin coatings/glazes and oils.

Application technique			Brushing	Rolling	
$ \begin{array}{c c} \hline $	Diluent		Adlerol-Terpentinölersatz (8002)		
	Diluent amount added (%)		0 - 5		
	Applied quantity per application (ml/m²)		80 - 100		
	The product is ready to use.				
	An additional 40 % material consumption is to be expected on rough sawn timber.				
	The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.				
	For good thorough drying, the recommended application quantities must be adhered to. Excessive layer thicknesses lead to a considerable drying delay!				
Drying times (at 23 °C and 50 % rel. humidity) C 12h	Recoatable after	approx.	ox. 12 h		
	The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.				
	Lower temperatures and/or high level of atmospheric humidity can increase the drying time.				
	On types of woods rich in extracts (such as oak, iroko), drying may be delayed.				
Cleaning the working equipment	With Adlerol-Terpentinölersatz (7231) immed	liately a	after use.		
	SUBSTRATE				
Type of substrate	Softwoods and hardwoods as well as plywo for the exterior, such as, for example, solid v timber (GLT or Glulam) and solid structural t	wooder	n boards, glue		
Substrate property	The substrate must be dry, clean, capable separating substances such as grease, wax, wood dust, as well as tested for suitability fo	silicon	e, resin etc. ar		
	A prerequisite for ensuring long durability basic principles of constructional wood prese	of the ervatio	coating is to n.	observe the	

	Please observe the additional documents:ÖNORM B 2230-1
	• ÖNORM B 3430-1
	• DIN 18363
	BFS data sheet no. 18.
Wood moisture	Hardwoods: 12 ± 2 %
	Softwoods: 15 ± 2 %
Substrate preparation	For optimal durability we recommend to sand smooth wooden surfaces with grain size 80 – 120 in the direction of the fibre, clean thoroughly and remove wood extractives such as, for example, resins and resin pockets.
	Clean resin-rich woods and exotic woods with drying retardants with Nitro- Verdünner 8017 (8017).
	Treat algae, green deposits or mould in outdoor areas with Aviva Fungisan (8308).
	COATING SYSTEM
Impregnation	If necessary, impregnate outdoors once with Pullex Imprägnier-Grund (4436) (applies to timbers of durability class 3-5 according to EN 350) to protect against blue stain, fungal decay and insect infestation.
	Intermediate drying time: approx. 12 hours
	Use wood preservatives safely. Always read the label and observe the respective technical data sheets of the products before use.
	Please follow our ARL 056 - Working guideline for the use of wood preservatives.
Primer coat	1 x Pullex Color (4403)
Intermediate sanding	Slight smooth sanding: Grit size 240
	Remove sanding dust.
Finishing coat	1 x Pullex Color (4403)
	MAINTENANCE
Care	The durability depends on several factors: these include particularly the type of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary.
	If required, remove dust and dirt from the still intact areas and paint 1 - 2 x with Pullex Color (4403) in the required colour shade.
	On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals must be expected.
Maintenance	Please follow our ARL 504 - Working guideline for coating non-dimensionally stable and limited dimensionally stable construction elements - Maintenance and Repair.
	Please follow our ARL 304 - Working guideline for coating dimensionally stable and limited dimensionally stable construction elements - Maintenance and repair.

	ORDERING INFORMATION	
Size of trading unit	750 ml, 2.5 l, 10 l	
Colour shades / Glosslevels	Standard colour(s): W10 Weiß, tönbar (50530) Rot (50533)	
Color 4You	Braun (50535) Gelb (50532) RAL6005 (50536)	
	Other colour shades can be obtained using the ADLER colour mixing system Color4You.	
	Base paint(s): Pullex Color W10 Weiß, tönbar (50530) Pullex Color Basis W20 (50531) Pullex Color Basis W30 (50537)	
	It is recommended to prepare a trial colour sample on the original substrate using the coating system selected in order to assess the final colour shade.	
	In order to ensure uniformity of the colour shade, use only material with the same batch number on a given surface.	
	Please consume blended products within 3 months.	
	Please observe our ARL 800- Working guideline for working (including care and maintenance) with ADLER Mix, PUR Mix and Color4You dosing machines.	
Supplementary products	Adlerol-Terpentinölersatz (7231) Aviva Fungisan (8308) Nitro-Verdünner 8017 (8017) Pullex Bodenöl (4402) Pullex Imprägnier-Grund (4436)	
	Please refer to the corresponding technical data sheets of the products.	
	FURTHER DETAILS	
Durability / storage	Min. 5 year(s) in the original sealed containers.	
mit mit	Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).	
	We recommend to transfer the contents of open containers to smaller ones in order to prevent gelling / skin formation.	
	Close opened containers well and use up the content as soon as possible.	
Technical specifications	VOC content of the ready-to-use mixture: Limit value according to Directive 2004/42/EC for Pullex Color (Cat A/e): 400 g/l. Pullex Color contains a maximum of 380 g/l VOC.	
Giscode	BSL20	
Declaration of ingredients according to VdL-RL 01	alkyd resins / inorganic white and coloured pigments / organic pigments , aliphatic compounds / interface additives / rheology additives / wetting agent / light stabilisers / anti-skin agent / drying agents (siccatives) , biocides	
Safety information	During sanding use P2 / P3 dust filter.	
	If the product comes into contact with your eyes, rinse immediately with water and consult a doctor!	
	Keep out of the reach of children.	

Ensure good ventilation during application and drying.

During work, do not eat, drink or smoke.

Repeated contact can lead to chapped or cracked skin.

Do not allow to enter drains, water courses or soil.

Only dispose of empty containers for recycling. Dried material leftovers can be disposed of as household waste. Dispose of liquid material residues at the recycling center or the mobile collection of harmful substances.

When using cloths that have been soaked with oxidative drying products, there is a risk of spontaneous combustion! Spread soaked cloths out and let them dry; it is necessary to store them in sealed metal containers or under water.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com**.