

ADLER Aqua-Nova PRO Spray M

4154000015 ff

Water-based pigmented matt coating system for professional use

	PRODUCT DESCRIPTION	
General	Water-based, non-yellowing, opaque coating system for indoors and outdoors. Excellent resistance to weathering and UV, high scratch resistance, high level of block resistance and high chemical resistance.	
	The low-odour and environmentally friendly product is excellent to process and has an optimal flow.	
Special properties and standards EMISSIONS DANS L'AIR INTÉRIEUR A H B C	ÖNORM EN 71-3 Safety of toys; migration of certain elements (free of heavy metals)	
	 DIN 53160-1 and DIN 53160-2 perspiration and saliva-proof properties 	
	 French ordinance DEVL1104875A regarding the marking of construction coating products for their emission of volatile pollutants: A+ 	
Application areas	 Coating on primed wood indoors and metal, hard PVC, as well as intact old coatings indoors and outdoors. 	
	 We recommend ADLER Ferro GSX 54120 ff for sheet metal roofs and steel constructions with extreme weathering. 	
	 Coat horizontal sheet metal outdoors with ADLER Ferrocolor 54111 ff or ADLER Ferro GSX 54120 ff. 	
	Please observe the relative technical data sheets of the products.	
	PROCESSING	
Instructions for use	Please stir the product before use.	
4 1	 The temperature of the product and object, and the room temperature must be at least + 10 °C. 	
	• The optimal conditions for use are between 15 $-$ 25 °C with a relative atmospheric humidity between 40 $-$ 80 %.	
	The flow of resin cannot be avoided based on the coating method.	

02-20 (supersedes 02-19) ZKL 4154

ADLER-Werk Lackfabrik, A-6130 Schwaz

Use sealing profiles and adhesive covering tapes for water-based

Phone: 0043/5242/6922-301, Fax: 0043/5242/6922-309, email: technical-support@adler-lacke.com

paints.

Application technique







Application method	Airless	Airless air- supported (Airmix, Aircoat, etc.)	Cup gun
Spray nozzle (ø mm)	0.28 or 0.33	0.28 or 0.33	1.8 – 2.0
Spray nozzle (ø inch)	0.011 or 0.013	0.011 or 0.013	-
Spraying angel (degrees)	20 – 40	20 – 40	-
Spraying pressure (bar)	80 – 100	80 – 100	3 – 4
Atomized air (bar)	-	0,5 – 1,5	-
Spraying distance (cm)	approx. 25		
Thinner	water		
Thinner amount added in %		-	0 – 5
Wet film (µm)	150 – 200		
Yield per application (g/m²)1)		300 – 400	
1) Yield including addition of thinner and loss while spraying			

The shape, the properties and moisture of the substrate affect the consumption/yield. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)



Recoatable	after approx. 6 hours
------------	-----------------------

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight (very quick drying).

Cleaning the working equipment



With water immediately after use.

To remove dried paint residues we recommend using ADLER Aqua-Cleaner 80080 (diluted 1:1 with water) or ADLER Abbeizer Express 8313000300.

SUBSTRATE

Type of substrate

Wood, wooden materials, metal as well as hard PVC

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

Please observe and follow ÖNORM B 2230 Part 1.

See also VOB, Part C, DIN 18363, Paragraph 3; painting and coating work.

Any coatings that cannot be recoated must be removed thoroughly.

Wood moisture

Hardwoods: 12 % +/- 2 %

Softwoods: 15 % +/- 2 %.

Preparation of the substrate

Wood and wood-based materials

Round off any sharp edges, remove wood extractives such as, for example, resins and pitch pockets.

Wood sanding with grit size 120 - 150

Iron and steel

Remove rust down to bare metal. Thoroughly remove greasy or oily impurities using ADLER Entfetter (degreaser) 80394.

Zinc, aluminium and other non-ferrous metals

Sand until matt with abrasive fleece and ADLER Entfetter 80394.

Hard PVC and coatable plastics

Sand until matt with abrasive fleece and ADLER Entfetter 80394.

Old coatings

Sand intact old coatings with grit size 120 and clean. Remove old coatings that cannot be recoated.

Please observe the relative technical data sheets of the products.

COATING SYSTEM

Primer

Wood and wood-based materials, indoors

1 x ADLER Aqua-Isoprimer PRO Spray Weiß 4153050000

Iron and steel, indoors

1 x ADLER Aqua-Multiprimer PRO Spray Weiß 4152050000

Iron and steel, outdoors

1 x ADLER Unigrund LM 54065 ff

or

1 x ADLER 2K-Epoxi-Grund 68304 f

Stainless steel

Sand stainless steel very well until matt and prime within 60 minutes with ADLER 2K-Epoxi-Grund 68304 f.

Zinc, indoors

1 x ADLER Aqua-Multiprimer PRO Spray 4152050000

In the case of surfaces subject to low mechanical stress, priming can be omitted.

Aluminium and other non-ferrous metals, indoors

1 x ADLER Agua-Multiprimer PRO Spray 4152050000

Zinc, aluminium and other non-ferrous metals, outdoors

1 x ADLER Unigrund LM 54065 ff

or

1 x ADLER 2K-Epoxi-Grund 68304 f

Anodised aluminium

Sand anodised aluminium very well until matt and prime within 60 minutes with ADLER 2K-Epoxi-Grund 68304.

Hard PVC and coatable plastics

Indoors, the primer can be omitted.

Outdoors 1 x ADLER Aqua-Multiprimer PRO Spray 4152050000.

Due to the large number of plastic materials, an adhesion test is recommended.

Old coatings

No primer coating is required for intact old coatings, but the compatibility of the coating must be checked. Damaged areas in not intact old coats must be pre-treated according to the respective substrate. Coating system like new paint.

Please observe the relative technical data sheets of the products.

Intermediate sanding



Sand primed surface with grit size 240.

Remove sanding dust.

Finishing coat

1 x ADLER Aqua-Nova PRO Spray M 4154000015 ff

MAINTENANCE & RENOVATION

Maintenance and renovation

The durability depends on several factors: these include particularly the type of weathering, constructional protection, mechanical stress and the choice of colour applied. To obtain long durability, preservation work is necessary in time. Therefore, we recommend annual maintenance.

If required, remove dust and dirt from the still intact areas and paint once with ADLER Aqua-Nova PRO M 4136000015 ff.

Please observe the relative technical data sheets of the products.

ORDERING INFORMATION


Size of trading unit

4 I, 18 I

Colour shades / degrees of gloss

ADLER Aqua-Nova PRO Spray M 4154049100 Weiß, tingable

Other colour shades can be obtained using the ADLER colour mixing system Color4You.



Base paints:

Base W15 4154000015 Base W20 4154000020 Base W30 4154000030

- In order to ensure uniformity of the colour shade, use only material having the same batch number on a given surface.
- It is recommended to prepare a trial colour sample on the original substrate using the coating system selected in order to assess the final colour shade.
- Please consume blended products within 3 months.

Supplementary products

ADLER Ferro GSX 54120 ff

ADLER Ferrocolor 54111 ff

ADLER 2K-Epoxi-Grund 68304 f (anodised aluminium and stainless

steel)

ADLER Aqua-Multiprimer PRO Spray 4152050000 (metal)

ADLER Aqua-Isoprimer PRO Spray 4153050000 (wood)

ADLER Aqua-Nova PRO M 4136000015 ff

ADLER Abbeizer Express 8313000300

ADLER Entfetter 80394 ADLER Aqua-Cleaner 80080

OTHER INSTRUCTIONS

Durability / storage

At least 1 year in the original sealed containers.





Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Technical specifications

VOC content

EU threshold for ADLER Aqua-Nova PRO Spray M (cat. A/d): 130 g/l (2010). ADLER Aqua-Nova PRO Spray M contains a maximum of 80 g/l VOC.

Safety-related information



Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.

The product is only suitable for industrial and professional use.

Inhaling paint aerosols whilst spraying must generally be avoided. This is ensured by correctly using a breathing mask (combination filter A2/P2 – ÖNORM EN 14387 /EN 143).