

Pigmofix G

8122

Additive for pigmented ADLER 2-component PUR furniture coatings for professional and industrial use

PRODUCT DESCRIPTION


Product numbers

90699

General

Additives for solvent-based two-component PUR coatings to achieve good moisture protection of the coating and to increase permanent adhesion to glass.

Application area



Additive for Pigmopur G50 (2406) and Aduro Pigmotop (2514) for the rear coating of glass parts whose edges are protected from direct contact with moisture due to their design (e.g. wooden frames).

Please refer to the corresponding technical data sheets of the products.

PROCESSING

Processing instructions



- Please shake the product before use.
- Please follow our **ARL 143 - Working guidelines for reverse-side glass coating with furniture coatings.**

Quantity to be added



5% on the coating (excluding hardener and thinner)

Carefully work the product into the coating-hardener mixture under stirring, ensuring it is completely free of lumps.

Stir Pigmofix G (8122) into the coating system at the same time as the corresponding amount of hardener.

Pigmopur G50 (2406) and Aduro Pigmotop (2514) are cured with 20% PUR-Hardener 8419 (8419000210) for this area of application.

Cleaning the working equipment



With DD-Verdüner 8519 (8519) or Waschverdünner (8501) immediately after use.

ORDERING INFORMATION

Size of trading unit

200 g

FURTHER DETAILS

Durability / storage



Min. 1 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Close opened containers well and use up the content as soon as possible.

Safety information



The product is only suitable for the industrial and professional use.

It is recommended to use safety gloves and safety glasses while processing.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet.

The current version can be accessed on the Internet at www.adler-lacke.com.