

Pullex 2in1-Holzlasur

4477

Solvent-based impregnation glaze for DIY and trade

PRODUCT DESCRIPTION

General

Universal, solvent-based wood glaze, free from aromatic compounds and cobalt, formulated with long-oil alkyd resins, for wood in outdoor areas. Stand-out features of this open-pore product include very good protection against water, long-term durability and uniform degradation when exposed to weathering.

Special properties and standards

- The coating is protected against blue stain and mould by a biocidal active substance.

Active substance:

2.0 g/kg (0.20 %) 3-Iod-2-propinylbutylcarbamate

Application area



For non-dimensionally stable and limited dimensionally stable timber components for exterior use, such as e.g. wooden houses, timber cladding, canopies, profile boards, window shutters, balconies, gates.

PROCESSING

Processing instructions



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least + 5 °C.
- The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %.
- Do not process it under conditions of intense sunlight, rain, extremely high humidity, strong wind or pending frost.
- For new timber components we recommend an all-over coating.
- Due to the system, glazes are only limitedly step-resistant and therefore require more frequent maintenance.
- Resin flow cannot be avoided by the coating.
- Water-soluble wood extracts can be leached particularly by driving rain. This can be minimized by an all-over coating and additional sealing of the end grains.
- Residual plaster (high level of alkalinity) or ferrous dust (rust formation) may lead to black discoloration on larch wood and other types of wood rich in extracts.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems as well as to impairments with regard to weathering and color stability.

2-0 IMC 4477 | 05/25 | replaces 1-0

ADLER-Werk Lackfabrik, A-6130 Schwaz

Fon: +43/5242/6922-190, Fax: +43/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions are based on the current state of knowledge and are intended to advise the buyer/user to the best of our knowledge, but must be individually adapted to the areas of application and processing conditions. The buyer/user is responsible for deciding on the suitability and use of the supplied product, which is why we recommend that a sample be produced to check the suitability of the product. In all other respects, our General Terms and Conditions of Sale apply. All previous data sheets lose their validity with this edition. We reserve the right to make changes to container sizes, color shades and available gloss levels.

- Please follow our **ARL 500 - Working guideline for coating non-dimensionally stable and limited dimensionally stable construction elements – General part.**
- Please follow our **ARL 505 - Working guideline for alkyd resin coatings/-glazes and oils.**

Application technique



	Brushing
Applied quantity per application (ml/m²)	80 - 100

The product is ready to use.

An additional 40 % material consumption is to be expected on rough sawn timber.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

For good thorough drying, the recommended application quantities must be adhered to. Excessive layer thicknesses lead to a considerable drying delay!

Drying times

(at 23 °C and 50 % rel. humidity)



Recoatable	12 h
------------	------

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

On types of woods rich in extracts (such as oak, iroko), drying may be delayed.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Cleaning the working equipment



With Adlerol-Terpentinölersatz (7231) immediately after use.

SUBSTRATE

Type of substrate

Softwoods and hardwoods as well as plywood materials, which are suitable for the exterior, such as, for example, solid wooden boards, glued laminated timber (GLT or Glulam) and solid structural timber (SST).

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

A prerequisite for ensuring long durability of the coating is to observe the basic principles of constructional wood preservation.

Please observe the additional documents:

- ÖNORM B 3430-1
- ÖNORM B 2230-1
- DIN 18363
- BFS data sheet no. 18.

Wood moisture

Hardwoods: 12 ± 2 %

Softwoods: 15 ± 2 %

Substrate preparation	For optimal durability we recommend to sand smooth wooden surfaces with grain size 80 – 120 in the direction of the fibre, clean thoroughly and remove wood extractives such as, for example, resins and resin pockets. Round off any sharp edges. Clean resin-rich woods and exotic woods with drying retardants with Nitro-Verdünner 8017 (8017). Sand and/or leach intact old coating. Remove old coatings that cannot be recoated. Treat algae, green deposits or mould in outdoor areas with Aviva Fungisan (8308).
COATING SYSTEM	
Impregnation	If necessary, impregnate outdoors once with Pullex Imprägnier-Grund (4436) (applies to timbers of durability class 3-5 according to EN 350) to protect against blue stain, fungal decay and insect infestation. Intermediate drying: approx. 12 hour(s) Use wood preservatives safely. Always read the label and observe the respective technical data sheets of the products before use.
Primer coat	1 x Pullex 2in1-Holzlasur (4477) Intermediate drying: approx. 12 hour(s)
Finishing coat	1 x Pullex 2in1-Holzlasur (4477)
MAINTENANCE	
Care	The durability depends on several factors: these include particularly the type of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary. If required, remove dust and dirt from the still intact areas and paint 1 – 2 x using Pullex 2in1-Holzlasur (4477). On deep-pored hardwoods, e.g. Oak, Iroko, shorter maintenance intervals must be expected.
Maintenance	Please follow our ARL 504 - Working guideline for coating non-dimensionally stable and limited dimensionally stable construction elements - Maintenance and Repair.
ORDERING INFORMATION	
Size of trading unit	0.75 l, 2.5 l and 5 l
Colour shades / Glosslevels	Standard colour(s): Farblos (4477000200) Eiche (4477050044) Lärche (4477050045) Kiefer (4477050046) Nuss (4477050049) Palisander (4477050050) The final colour is basically obtained from the inherent colour of the wood, the applied quantity, the colour of the impregnation and the colour of the finishing coat. It is recommended to prepare a trial colour sample on the original substrate using the coating system selected in order to assess the final colour shade.

In order to ensure uniformity of the colour shade, use only material with the same batch number on a given surface.

Apply exclusively pigmented colour shades to ensure a good weather resistance.

Medium colour shades have the best weathering resistance; colours that are too light or too dark should be avoided if exposed to extreme weathering.

When brightening the standard colour shades with Pullex 2in1-Holzlasur colourless (4477), shorter renovation intervals must be expected (reduced UV protection). Therefore, Weide or Eiche should be used to brighten darker colour shades.

Supplementary products

Adlerol-Terpentinölersatz (8002)
Aviva Fungisan (8308)
Nitro-Verdünner 8017 (8017)
Pullex Imprägnier-Grund (4436)

Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS

Durability / storage



Min. 5 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Close opened containers well and use up the content as soon as possible.

Technical specifications

VOC content of the ready-to-use mixture: Limit value according to Directive 2004/42/EC for Pullex 2in1-Holzlasur (Cat A/f): 700 g/l.
Pullex 2in1-Holzlasur contains a maximum of 660 g/l VOC.

Giscode

BSL40

Declaration of ingredients according to VdL-RL 01

alkyd resins / aliphatic compounds / inorganic white and coloured pigments / organic pigments / surface additive / glycol ether / wetting agent / drying agents (siccatives) / light stabilisers / anti-skin agent / 3-iodo-2-propynylbutylcarbamate

Contains 3-iodo-2-propynyl butylcarbamate. May cause allergic reactions.

Information for allergy sufferers under telephone no. +43 5242 6922-713.

Safety information



When using cloths that have been soaked with oxidative drying products, there is a risk of spontaneous combustion! Spread soaked cloths out and let them dry; it is necessary to store them in sealed metal containers or under water.

When sanding, use at least a P2 dust filter as personal safety equipment to protect against abrasive and wood dust. In case of hardwood (especially for Beech, Oak) a dust filter P3 is recommended.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.